

ABSOLUTE Aligner

The Difference is Clear.



A PORTFOLIO OF PREMIUM MATERIALS

Prodways' exclusive MOVINGLight® technology, based on photo-polymerization of liquid resin via moving DLP® projectors, is designed to work with premium acrylate and hybrid resins to deliver unequalled levels of precision and productivity for a large array of applications in industries such as dental, medical, aerospace, investment casting, molding, and R&D centers.


INNOVATION AND EXPERTISE

Prodways is constantly innovating to develop new materials with unique mechanical, physical, and aesthetic properties, supported by internal R&D teams at Prodways Materials as well as strategic partners.

Our experts also support customer research and innovation for the development of new materials to push MOVINGLight® 3D printing technology into new territories.

A REVOLUTIONARY NEW MATERIAL FOR THE INDUSTRIAL PRODUCTION OF CLEAR ALIGNER MODELS

PLASTCure Absolute Aligner : Absolute transparency - Absolute quality - Absolute optimization



PLASTCure ABSOLUTE ALIGNER - KEY FEATURES

Ultra Smooth Surface Finish

Achieve **precise thermoforming results** without sacrificing machine quality.

Optimized For Scanning

Color specifically engineered for **easy scannability** to ease QC protocol.

Outstanding Accuracy & Clarity

Helping you achieve **superior and repeatable results** with optimal clarity.

Thanks to its advanced formulation, Absolute Aligner has **NO sedimentation**, removing the need for frequent stirring and saving you time. Learn more about how this **revolutionary new material** can help you produce the **most transparent clear aligner** on the market.

PLASTCure ABSOLUTE ALIGNER - SPECS

ABSOLUTE ALIGNER LIQUID RESIN

Appearance	Blue
Compatible application	Aligner models
Compatible machines	LD10 and LD20 Dental models
Applicable layer thickness	[50 - 175] µm
Viscosity	350 - 450 mPas at 28°C
Density	1.08 g/cm³
Flexural Modulus	[1900 - 2100] MPa
Flexural Strength	[80 - 90] MPa
Strain at Break	[6 - 9]%
Hardness	[80 - 85] Shore D
Tensile Modulus	[2200 - 2500] MPa
Tensile Strength	[46 - 50] MPa
Elongation at Break	[4 - 6]%
Water Absorption	[1.3 - 1.5]%
HDT	[66 - 70] °C at 0.46 MPa
Recommended post-processing equipments	Spinner Aligner Cleaning station / PCU90 with Nitrogen or IPA cleaning solutions with PCU90

WWW.PRODWAYS.COM

USA | Boston
316 Daniel Webster Hwy, Merrimack, NH 03054
+1 603-429-9700

Germany | Frankfurt
Raiffeisenstr. 8a - 61169 Friedberg
+49 (0)6031 / 7283-0

France | Paris
ZI Des Garennes - 1, rue Chappe - 78130 Les Mureaux
+33 (0)1 30 90 44 12